COMPRESSED FIBER SHEET



PRODUCT PROFILE

SF 5000 is an NBR bound sheet reinforced with carbon and aramid fibers. SF 5000 is suitable for use in a wide range of industrial applications including oils, fuels, steam, water and dilute acids. SF 5000 is especially suitable for sealing caustic liquors. Properties based on 1/32" thick material, except as otherwise noted.

SERVICE

Max T (at min. thickness) 824°F (440°C)

Max P (at min. thickness) 2030 psi (14.0 MPa)

pH Range 3 - 14

PHYSICAL PROPERTIES

Color Black

Density 100 lb/ft³ (1.60g/cc)

Sheet Thickness 1/64" - 1/8" (0.50 mm - 3.20 mm)

Sheet Size 60" x 60", 60" x 120" (1.50 m x 1.50 m, 1.5 m x 3.0 m

MECHANICAL PROPERTIES (ASTM F152)

Cross Grain Tensile 2625 psi (18.1 MPa)
With Grain Tensile 7005 psi (48.3 MPa)

IMMERSION PROPERTIES (ASTM F146)

Thickness Increase Oil #3 @ 300°F 3%

Fuel B @ 70 - 85°F 5%

Weight Increase Oil #3 @ 300°F 10%

Fuel B @ 70 - 85°F 12%

SEALING PROPERTIES

ASTM F36J Compressibility 7.5%

Recovery 64%

ASTM F37A Fuel A @ 50 psi & 1000 psi Gasket Stress 0.87 mL/hr

ASTM F38 Creep Relaxation 22.2%

BS 7531 Nitrogen Gas Permeability 0.05 mL/min



Compressed Fiber Sheet




PRODUCT PROFILE

DESIGN INFORMA	TION			
Gasket Constants	m	3.7		
	у	3335 psi (23.00 MPa)		
PVRC Constants (1/16" thick)	Gb	N/A		
	а	N/A		
	Gs	N/A		
Recommended Surface Finish	125-250 μin (3.2 - 6.3 μm)			
Dielectric Strength	N/A			
ASTM Callout	712120M6†	† some digits may be chosen differently		

PRESSURE CONTAINMENT AND TEMPERATURE

SF 5000 Thickness (in.)	0.020	0.030	1/16	0.080	1/8
Max. Temperature (°F)	824	806	752	662	392
Max. Pressure (psi)	2030	1800	1305	1015	435

NOTE: Above pressure/temperature cannot be used simultaneously.



Major Manufacturing Plants

Flexitallic L.P. 6915 Highway 225 Deer Park, Texas 77536 Tel: 281-604-2400 Fax: 281-604-2415

Flexitallic Ltd. P.O. Box 3, Dewsbury Rd., Cleckheaton West Yorkshire BD19 5BT Tel: 44 1274 851 273

Fax: 44 1274 851 386

This Data Sheet relates to the material as supplied. The information contained herein is given in good faith, but no liability will be accepted by the Company in relation to same. The acquisition of additional information may necessitate revisions to parts or all of this Data Sheet, and such infor-mation will be supplied as it becomes available.

As the Company's products are used for a multiplicity of purposes, and as the Company has no control over the method of their application or use, the Company excludes all conditions or warranties, express or implied, by statue or otherwise, as to their products and/or their fitness for any particular purpose. Any technical co-operation between the Company and the Customer is given for the Customer's assistance only and without liability on the part of the Company.

